



ISO-9001 Registered Quality System.
ISO-21469 Compliant.

Sales, Service & Distribution Center

Newark, NJ 07105
Phone: 973-589-9150 Fax: 973-589-4432

Manufacturing, Sales, Service & Distribution Center

Toledo, OH 43605
Phone: 419-691-2491 Fax: 419-693-3806

Sales and Tech Service Support

Phone: 1-800-733-4755

LUBRIPLATE Neptune Launching Slip Coat

LUBRIPLATE Neptune Launching Slip Coat is to be applied over the hardened Base Coat layer. Slip Coat is extremely water resistant and can be used over a wide temperature range.

Typical Properties

NLGI No.	3½
Penetration Range 60 Strokes Worked	210 - 250
Thickener	Calcium Soap
Dropping Point	200°F
Specific Gravity	0.93
Color	Orange
Texture	Smooth

Slip Coat is applied from the drum as is. It should not be heated prior to application. After the Base Coat has cooled, the Slip Coat is spread on to the desired thickness. Typical thickness is ¼" to ½". Slip Coat is orange in color making it distinguishable from the Base Coat.

Coverage

<u>Thickness In Inches</u>	<u>Pounds Required to Cover 1 Square Foot (Approx.)</u>	<u>Drum (About 400 lbs.) Will Cover Square Feet (Approx.)</u>
1/8	.60	666
1/4	1.20	333
1/2	2.37	169

Packaging Available

400 lb. Drums

Part No.

L0215-040