



EXECUTIVE OFFICE: NEWARK, NJ 07105
PHONE: 973-589-9150 FAX: 973-589-4432
MIDWEST OFFICE: TOLEDO, OH 43605
PHONE: 419-691-2491 FAX: 419-693-3806
TECHNICAL SERVICE PHONE NO. 800-347-5343

FISKE's Alumaplex EP-2

Typical Tests

Soap Base	Aluminum Complex
NLGI Grade	2
Penetration Range, 60 Strokes Worked	265 – 295
Dropping Point	485°F
Mineral Oil Viscosity SUS @ 100°F	1000
SUS @ 210°F	73
Four Ball EP Test OK Load	280 kg.
Weld Load	300 kg.
Flash Point of Mineral Oil	420°F
Pour Point of Mineral Oil	- 15°F
Color	Amber
Character	Smooth & Tacky