



EXECUTIVE OFFICE: NEWARK, NJ 07105
PHONE: 973-589-9150 FAX: 973-589-4432
MIDWEST OFFICE: TOLEDO, OH 43605
PHONE: 419-691-2491 FAX: 419-693-3806
TECHNICAL SERVICE PHONE NO. 800-347-5343

FISKE's Moly EP-00/150

Typical Tests

Type of Thickener	Lithium
Worked Penetration	390 – 420
NLGI No.	00
Dropping Point	368°F
Mineral Oil Viscosity @ 100°F @ 210°F	800 SUS 75 SUS
Pour Point of Mineral Oil	0°F
Flash Point of Mineral Oil	450°F
Timken OK Load	45 lbs.
Color	Steel Grey
Character	Smooth
Contains Technical Fine Molybdenum Disulfide	