



Sales, Service & Distribution Center

Newark, NJ 07105

Phone: 973-589-9150 Fax: 973-589-4432

Manufacturing, Sales, Service & Distribution Center

Toledo, OH 43605

Phone: 419-691-2491 Fax: 419-693-3806

Sales and Tech Service Support

Phone: 1-800-733-4755

FISKE's 493-A Lubricant

Typical Tests

Type of Thickener	Lithium 12-Hydroxy Stearate
Thickener %	6 - 12%
Filler Content (Polyethylene)	2.5 - 7%
Penetration (60 Strokes Worked)	265 - 295
N.L.G.I. Grade	2
Change in Penetration 60 to 100,000 Strokes	15% Increase Maximum
Dropping Point	175°C Minimum
Mineral Oil Viscosity cSt @ 100°C	12.9 - 16.7
cSt @ 40°C	177 - 190
Fire Point	250°C Minimum
Flash Point	225°C Minimum
Pour Point	-15°C Maximum
Water Washout	7.0% Maximum
Oxidation Stability after 100 hours pressure drop	69 kPa Maximum