



EXECUTIVE OFFICE: NEWARK, NJ 07105
PHONE: 973-589-9150 FAX: 973-589-4432
MIDWEST OFFICE: TOLEDO, OH 43605
PHONE: 419-691-2491 FAX: 419-693-3806
TECHNICAL SERVICE PHONE NO. 800-347-5343

FISKE'S Art & Mil Grease

Typical Tests

Type of Thickener	Anhydrous Calcium
Percent of Thickener	8 - 13%
Worked Penetration 60 Strokes @ 77°F (ASTM D-217)	265 - 295
NLGI No.	2
Mineral Oil Properties:	
Viscosity @ 40°C	13.0 - 17.0 mm ² /s
Viscosity @ 100°C (ASTM D-445)	1.8 - 4.2 mm ² /s
Pour Point (ASTM D-97)	-50°F/-46°C
Flash Point (ASTM D-92)	325°F/163°C
Dropping Point (ASTM D-566)	280°F/138°C
Cold Test of Lubricant	-60°F/-51°C
Oxidation Stability Drop 100 Hours (ASTM D-942)	5 psi/34.5 kPa
Color	Amber (translucent)
Character	Smooth
Rust Preventative Properties 48 hrs. @ 52°C. (ASTM D-1743)	Pass, no corrosion

Meets and is an approved source for the following Ford Specifications:

ESB-M1C163-C
WSB-M1C163-D