



ISO-9001 Registered Quality System.
ISO-21469 Compliant.

Sales, Service & Distribution Center
Newark, NJ 07105
Phone: 973-589-9150 Fax: 973-589-4432

Manufacturing, Sales, Service & Distribution Center
Toledo, OH 43605
Phone: 419-691-2491 Fax: 419-693-3806

Sales and Tech Service Support
Phone: 1-800-733-4755

PRODUCT DATA

LUBRIPLATE FGL-CC

"This product is certified OU Kosher Pareve"
"This product is Halal certified"

*NSF International H-1 Registered
NSF ISO21469 Certification

DESCRIPTION

LUBRIPLATE FGL-CC has been developed specifically for use in centralized and automatic lubrication systems on high-speed can-closing equipment.

APPLICATIONS

LUBRIPLATE FGL-CC has years of successful field service in the beverage industry. LUBRIPLATE Division has worked closely with both original equipment manufacturers and beverage processors to ensure that LUBRIPLATE FGL-CC meets the severe demands of this application. LUBRIPLATE FGL-CC can also be used in other equipment where centralized lubrication systems are used such as fillers and packaging equipment.

ADVANTAGES

- ⇒ Unique thickening structure resists oil separation often encountered using conventional food grade greases.
- ⇒ High temperature stability and oxidation resistance.
- ⇒ Excellent resistance to water washout.
- ⇒ Provides outstanding rust and corrosion protection.
- ⇒ Effective anti-wear additives result in superior wear protection.
- ⇒ Excellent batch-to-batch consistency eliminates grease hardening which can be a common problem for many food grade greases while in storage.

STORAGE RECOMMENDATIONS

1. Products should be stored between 40°F-120°F.
2. Products should be stored in a dry covered environment.
3. Products should not be stored in warm, direct sunlight.
4. improper storage conditions can significantly alter the shelf life of the product. Such conditions would include temperature, moisture, open containers, etc.

Typical Test Data

PROPERTY	TEST METHOD	TYPICAL RESULTS*
Thickener		Aluminum Complex
Penetration Range 60 Strokes	ASTM D-217	370 - 410
NLGI No.		0/00
Dropping Point	ASTM D-566	450°F
Four Ball Wear Test	ASTM D-2266	0.38 mm
Water Washout (175°F)	ASTM D-1264	<8%
Oxidation Stability 100 hours	ASTM D-942	2.0 psi
Base Fluid Properties: Viscosity		Proprietary
Flash Point °F/°C	ASTM D-92	500°F
Pour Point °F/°C	ASTM D-97	0°F
Color	Visual	White
Texture	Visual	Smooth

PACKAGING AVAILABLE

	<u>Part No.</u>
35 lb Pail	L0229-035
120 lb. Quarter Size, Drum	L0229-039
415 lb. Full Size, Drum	L0229-040

***NSF International H-1 Registration No. 043530**
(Meets former USDA 1998 Guidelines)

*Registered H-1 by NSF International for use in food processing facilities as a lubricant or anti-rust agent on equipment in which there may be incidental contact involving the lubricated part and the edible product.

"LUBRIPLATE FGL-CC contains no components derived from TSE/BSE relevant animal species; therefore, it is compliant with the requirements of the TSE Note for Guidance EMA/410/01 Rev. 3 July 2011".

