



ISO-9001 Registered Quality System.
ISO-21469 Compliant.

Sales, Service & Distribution Center

Newark, NJ 07105
Phone: 973-589-9150 Fax: 973-589-4432

Manufacturing, Sales, Service & Distribution Center

Toledo, OH 43605
Phone: 419-691-2491 Fax: 419-693-3806

Sales and Tech Service Support

Phone: 1-800-733-4755

LUBRIPLATE TURBINE OILS

LUBRIPLATE Turbine Oils have been specifically formulated for steam turbine applications. In addition to offering protection against oxidation, rust and foam, LUBRIPLATE Turbine Oils also readily separate from moisture.

The LUBRIPLATE Turbine Oil 32 meets the requirements of General Electric Specification GEK-46506B.

Typical Tests

32

Viscosity	
SUS @ 100°F	152
SUS @ 210°F	44
cSt @ 37.8°C	32
cSt @ 99°C	5.4
ISO VG	32
Viscosity Index	113
Flash Point	390°F/199°C
Fire Point	440°F/227°C
Pour Point	-10°F/-23°C
Water Content	Less than 0.01%
Rust Test (ASTM D-665)	Pass; No Rust
Specific Gravity	0.864
Neutralization Value	0.20 mg KOH/g (max)
Oxidation Test (ASTM D-943)	> 10,000 Hours
Color	L-1.5