



ISO-9001 Registered Quality System.  
ISO-21469 Certified

**Sales, Service & Distribution Center**  
Newark, NJ 07105  
Phone: 973-589-9150 Fax: 973-589-4432

**Manufacturing, Sales, Service & Distribution Center**  
Toledo, OH 43605  
Phone: 419-691-2491 Fax: 419-693-3806

**Sales and Tech Service Support**  
Phone: 1-800-733-4755

## PRODUCT DATA

# LUBRIPLATE SYNXTREME HTCO MAX

"OU Kosher Pareve" (Certification Pending)  
"Halal" (Certification Pending)

\*NSF International H-1 Registration (Pending)

## DESCRIPTION

LUBRIPLATE SYNXTREME HTCO MAX is a completely fluorinated synthetic lubricant specially formulated to provide effective long term lubrication to food plant equipment exposed to temperatures in excess of 500°F/260°C. The active lubricant is diluted with a non-flammable fluorosolvent that is approved for incidental food contact.

## ADVANTAGES

- ⇒ Excellent Thermo-oxidative Stability
- ⇒ Low Volatility
- ⇒ Excellent Compatibility with Plastics and Elastomers
- ⇒ Chemically Inert Towards Chemical and Fuels
- ⇒ Non-Flammable

## SAFETY

LUBRIPLATE SYNXTREME HTCO MAX does not contain hazardous ingredients. If fumes are generated at elevated temperatures, ventilation is required. See the Safety Data Sheet for additional safety related information on the grease.



## Typical Test Data

PROPERTY	TEST METHOD	TYPICAL RESULTS
Base Fluid Type		PFPE
Color	Visual	Clear
<b>Kinematic Viscosity:</b>		
@ 40°C	ASTM D-445	488 cSt
@ 100°C	ASTM D-445	46 cSt
Viscosity Index	ASTM D-2270	150
Absolute Viscosity, 25°C	CTM-4	2556 mPa·s
Density, 25°C	CTM-3	1.89 g/cc
Flash Point	ASTM D-92	None
Pour Point	ASTM D-97	-22°F/-30°C
Evaporation, 24h @ 150°C	CTM-1	0.00%
TGA Temp. @ 5% Weight Loss	ASTM D-972	790°F/421°C
Wear, 20 kg Load	ASTM D-4172	0.514 mm
<b>Properties of Fluorosolvent:</b>		
Vehicle	Report	Fluorosolvent
Concentration	Report	90%
Flash Point	ASTM D-92	None
Boiling Point	Report	131°F/55°C

## PACKAGING AVAILABLE

1 Gallon Bottle  
4 Gallon Plastic Pail

## Part No.

L1025-051  
L1025-064